

2010.3.17

神海 強力表

双樹化学工業(株)

号柄	デニール	直径	kg長さ	直線強力(ST)	結節強力(LF)	LF/ST
		mm	m/kg	kg	kg	%
# 1	220	0.16	40,000	1.83	1.56	85.2
1.5	330	0.20	26,500	3.00	2.30	76.7
2	440	0.23	20,000	4.20	3.70	88.1
2.5	550	0.26	16,500	5.20	4.20	80.8
3	660	0.28	13,000	6.20	5.10	82.3
4	880	0.33	10,000	8.00	6.90	86.3
5	1,100	0.37	8,000	9.00	8.00	88.9
6	1,320	0.40	7,000	10.00	9.00	90.0
7	1,540	0.44	6,000	12.00	10.00	83.3
8	1,760	0.47	5,000	13.50	11.00	81.5
10	2,200	0.52	4,000	17.00	13.70	80.6
12	2,640	0.57	3,400	20.00	16.00	80.0
14	3,080	0.62	2,900	23.50	18.50	78.7
16	3,520	0.66	2,500	27.00	20.50	75.9
18	3,960	0.70	2,200	30.00	23.00	76.7
20	4,400	0.74	2,000	33.00	25.50	77.3
22	4,840	0.77	1,800	36.50	28.00	76.7
24	5,280	0.81	1,600	40.00	30.50	76.3
26	5,720	0.84	1,500	43.00	33.00	76.7
28	6,160	0.87	1,400	46.20	35.50	76.8
30	6,600	0.90	1,300	48.00	38.00	79.2
35	7,700	0.97	1,150	56.00	44.00	78.6
40	8,800	1.04	1,000	64.00	50.00	78.1
50	11,000	1.17	800	80.00	60.50	75.6
60	13,200	1.28	650	95.00	72.00	75.8
65	14,300	1.33	630	103.00	78.00	75.7
70	15,400	1.38	600	110.00	82.00	74.5

2010.3.17

神海 強力表

双樹化学工業(株)

号柄	テニール	直径	kg長さ	直線強力(ST)	結節強力(LF)	LF/ST
		mm	m/kg	kg	kg	%
# 80	17,600	1.47	500	124	93	75.0
90	19,800	1.56	450	139	104	74.8
100	22,000	1.65	400	154	116	75.3
110	24,200	1.73	370	169	125	74.0
120	26,400	1.81	340	182	137	75.3
130	28,600	1.88	310	197	145	73.6
150	33,000	2.00	270	230	165	71.7
160	35,200	2.09	250	245	176	71.8
170	37,400	2.15	240	255	182	71.4
180	39,600	2.25	220	270	188	69.6
200	44,000	2.35	195	290	202	69.7
220	48,400	2.45	186	314	220	70.1
230	50,600	2.50	170	331	230	69.5
240	52,800	2.56	170	345	240	69.6
250	55,000	2.61	160	357	248	69.5
260	57,200	2.66	160	369	254	68.8
280	61,600	2.76	140	388	271	69.8
300	66,000	2.85	130	396	284	71.7
330	72,600	3.00	120	420	300	71.4
350	77,000	3.10	117	435	308	70.8
360	79,200	3.13	113	443	312	70.4
380	83,600	3.25	105	451	322	71.4
400	88,000	3.30	102	466	330	70.8
450	99,000	3.50	91	499	351	70.4